

Preparation of rifampicin/poly(d,l-lactide) nanoparticles for sustained release by supercritical assisted atomization technique

P.W. Labuschagne^{a,*}, R. Adamib,^{*} S. Liparotib, S. Naidoo^a, H. Swaia, E. Reverchon^{b,c}

^aPolymers & Composites, Council for Scientific & Industrial Research (CSIR), PO Box 395, Pretoria, South Africa

^bDepartment of Industrial Engineering, University of Salerno, Via Giovanni Paolo II, 132, 84084 Salerno, Italy

^cResearch Centre for Nanomaterials and Nanotechnology (NANOMATES), Salerno University, Salerno, Italy

Abstract

In this work supercritical assisted atomization (SAA) process was used for the co-precipitation of poly(d,l-lactide) (PDLLA) and rifampicin (RIF) as nanoparticles for sustained release applications. The effect of the variation of PDLLA/RIF ratio on co-precipitate characteristics was mainly investigated. The precipitated particles were analyzed in terms of their morphological, thermodynamic and crystallographic properties. In addition, loading efficiency and in-vitro release studies were conducted. Spherical PDLLA/RIF nanoparticles with mean diameter ranging from 123 to 148 nm were prepared. Loading efficiency was greater than 100% resulting in RIF loadings of 28.8 to 50.5%. X-ray diffraction revealed that the encapsulated RIFs in an amorphous state, while NMR spectra indicated no structural modifications after the SAA process. In-vitro release studies showed an initial burst release of 80–87% of total RIF loaded, necessary to suppress the generation of resistance by the microorganism, followed by first-order sustained release between 0.4 and 0.8 mg/L RIF per day over a period of 17 days.