

EVALUATION OF MECHANICAL PROPERTIES OF CALOTROPIS GIGANTEASTEM FIBER-REIN FORCED COMPOSITE MATERIAL

¹ARUNA.M, ²SUDHAKAR MUNIYASAMY

¹Mechanical Engineering Department, Velammal College of Engineering and Technology, Madurai, Tamil Nadu, INDIA

²CSIR Materials Science and Manufacturing, Polymers and Composites Competence Area, P.O. Box 1124, Port Elizabeth 6000, South Africa

E-mail: ¹maruna9@gmail.com, ²smuniyas@gmail.com

Abstract- The awareness in natural fiber reinforced composite materials is rapidly growing both in terms of industrial applications and fundamental research. Natural fibers have recently become attractive to researchers, engineers and scientists as an alternative reinforcement for fiber reinforced polymer (FRP) composites. Owing to their availability, low cost, good mechanical properties, high specific strength, non-abrasive, eco-friendly and bio-degradability characteristics, they are exploited as a replacement for the conventional fiber, such as aramid and carbon. Several chemical modifications are employed to improve the interfacial matrix-fiber bonding resulting in the enhancement of mechanical properties of the composites. Calotropis gigantea is a species of calotropis, native to Cambodia, Indonesia, Malaysia, Philippines, Thailand, Sri Lanka, India, China, Pakistan, Nepal, and tropical Africa. Its fiber was extracted manually from the plant's stem and treated chemically. The samples have been prepared by varying the fiber percentages and epoxy resin. Hybrid Composites are fabricated using raw calotropis gigantea stem fiber/glass with varying fiber weight percent 5:0 to 5:3 weight by using hand layup method. The fabricated specimens were cut as rectangular pieces according to the ASTM standards for conducting all tests. The purpose of this paper is to assess the tensile strength, impact strength, density and hardness of hybrid calotropis gigantea stem fiber reinforced composites. Results illustrate that the use of less than 12 gm glass fiber in this composite increases tensile strength, impact, density and hardness.

Keywords- Calotropis gigantea, Stem fiber, Composites, Mechanical properties, Epoxy resin.

I. INTRODUCTION

Sustainable development is progressively becoming a priority of governments and business sectors which is driven by growing environmental attentiveness. Much academic research explores new ways to create greener and environmentally friendlier materials for variety of applications ranging from aeronautic, automotive and construction industry. Natural fibers are renewable resources in many developing countries of the world. The interest in natural fiber-reinforced composite materials is rapidly growing their industrial applications and fundamental research [1, 2].

Calotropis gigantea is drought resistant, salt tolerant to a relatively high degree, grows wild up to 900 meters throughout the country [3] and prefers disturbed sandy soils with mean annual rainfall: 300-400 mm. Through its wind and animal dispersed seeds, it quickly becomes established as a weed along degraded roadsides, lagoon edges and in overgrazed native pastures. It has a preference for and is often dominant in areas of abandoned cultivation. It is assumed to be an indicator of over cultivation [4]. It is one of the few plants not consumed by grazing animals [5]. The bark is thick, rough and corky and a yellow-brown colour; twigs are green and fleshy and may have a covering of tomentum (white fur like hairs). The stem of calotropis gigantea is a source of natural cellulosic bast fibers wherein the commercially valuable properties like cellulose content, fiber strength and fiber elongation are found to be intermediate between that of cotton and linen.

Other than high tensile and abrasive strength, fibers from calotropis gigantea possess more weight per square meter than the cotton fibers. Since calotropis is a wildly growing shrub in major parts of India, its use as a source of excellent cellulose fibers might have enormous economical implications. This fiber has enough potential for replacing or supplementing other fibrous raw materials as reinforcing agent. Calotropis yields a durable fiber (commercially known as Bowstring of India) useful for ropes, carpets, fishing nets, and sewing thread.

The mechanical behaviour of a fiber-reinforced composite basically depends on the fiber strength and modulus, matrix strength, the chemical stability and the interface bonding between the fiber/matrix to enable stress transfer [6]. Polyester matrix based composites have been widely used in marine applications, in marine field the water absorption was an important parameter in degradation of polymer composites. The different mechanisms used to identify the degradation of material such as initiation, propagation, branching and termination [7].

Calotropis bast fiber is one of these types that have been extracted manually up to now. Some research article investigates the effect of new decorticator machine on properties of extracted fiber and compared with separated fibers manually. The mentioned decorticator machine was able to extract bast fiber without shattering stems and flowing latex. Some studied properties were morphological characterization, tensile properties (tensile strength, Young's modulus and strain) and density of fiber. The results indicated that machinery extraction

method had no significant effect on the fiber morphology[8].

Calotropis stem has valuable fibers with various applications in the industry. Since extraction found to be more complex, extraction machine with the capacity of 2 kg/h based on dried mass of barks and fibers was developed [9]. Calotropis gigantea fruit fiber reinforced composites was prepared and mechanically tested. The tensile strength increased with increase in fiber content. Further, the wear behavior of the calotropis gigantea fruit fiber composite were studied with increase in fiber content [10].

Several chemical modifications are employed to improve the interfacial matrix-fiber bonding resulting in the enhancement of mechanical properties of the composites. They determined the mechanical and machining characteristics of the calotropis gigantea fruit fiber composites which are found good [11]. Study on the mechanical properties of calotropis gigantea composites revealed very less than the flax fiber composites. The suitable coupling agent and its concentration can be used out to improve its mechanical properties [12]. The feasibility of applying two kinds of mudar (Calotropis gigantea) fibers, namely bark fibers and seed fibers, as an alternative raw material for fiber-reinforced composite (FRC) was investigated. The mechanical properties of the mudar bark fibers are: tensile strength 381 MPa, strain at break 2.1% and Young's modulus 9.7 GPa. In general, both types of fibers have enough potential for replacing other fibrous raw materials as reinforcing agent [13].

The objective of this work is to examine the fiber extraction from calotropis gigantea stem by retting method and the use of these fibers as reinforcement in polymer matrix. Calotropis gigantea stem fiber reinforced composites at various percentage volume of fiber are fabricated, tested and characterized to evaluate their mechanical properties.

II. EXPERIMENTAL DETAILS

2.1. Materials and Procedures

Calotropis plant is generally known as "Milkweed", which has lots of medical applications. Calotropis bast fiber was extracted manually from the plant's stem by retting process to reinforce in the polymeric matrix, calotropis plant, and calotropis bast fibers are shown in Fig.1, 2. The extraction of fibers involves retting process followed by decorticating. The stems of calotropis were cut at their base and immersed in water for one day. Later, they are removed; the fibers were stripped from the stalks by hand, washed and dried in the sun. After drying, any unnecessary matter that may still be adhering to them was removed manually. The extracted fibers are treated with 5% aqueous NaOH solution and used for composite making after

drying. Alkaline treatment or mercerization is one of the most used chemical treatments of natural fibers when used to reinforce thermoplastics and thermosets. The important modification done by alkaline treatment is the disruption of hydrogen bonding in the network structure, thereby increasing surface roughness. This treatment removes a certain amount of lignin, wax and oils covering the external surface of the fiber cell wall, depolymerises cellulose and exposes the short length crystallites.



Fig.1. Calotropis gigantea Plant



Fig.2. Calotropis gigantea fiber after mercerization

Addition of aqueous sodium hydroxide (NaOH) to natural fiber promotes the ionization of the hydroxyl group to the alkoxide. In alkaline treatment fibers are immersed in NaOH solution for the given period of time. Normality of NaOH solution is 0.5N.

Polymers generally act as a good binder for fibers as observed from the literature review. Availability has provoked Epoxy as the matrix material for this investigation. Epoxy resins are the most commonly used thermoset plastic in polymer matrix composites. Epoxy resins are a family of thermoset plastic materials which do not give off reaction products when they cure and so have low cure shrinkage. They also have good adhesion to other materials, good chemical and environmental resistance, good chemical properties and good insulating properties. The epoxy resins are generally manufactured by reacting epichlorohydrin with bisphenol.

2.1.1. HAND LAY-UP TECHNIQUE

The process is studied with a standard Response surface methodology design called a Central Composite Design (CCD) with three variables; eight cube points, four central points, six axial points and two center points in axial, in total 20 runs. Total numbers of experiments conducted with the combination of parameters are presented in Table 1. The CCD is used since it gives a comparatively accurate prediction of all response variable averages related to quantities measured during experimentation [14]. The response variables investigated are the Tensile strength, Impact strength, Hardness and density. The compositions of samples are given in Table 1.

Table 1: Central composite experimental design

Sample	Calotropis Fiber, gm	Epoxy resin gm	Glass Fiber gm
1	30	165.5	0
2	30	165.5	4.5
3	13.18	165.5	4.5
4	20	171	0
5	20	160	9
6	40	171	0
7	30	174.75	4.5
8	40	160	0
9	30	165.5	4.5
10	40	171	9
11	30	165.5	4.5
12	30	165.5	12.06
13	20	160	0
14	30	165.5	4.5
15	20	171	9
16	30	165.5	4.5
17	30	156.25	4.5
18	40	160	9
19	46.81	165.5	4.5
20	30	165.5	4.5

Hand lay-up is the simplest and oldest open molding method of the composite fabrication processes. It is a low volume, labor intensive method suited especially for large components, such as boat hulls. Glass or other reinforcing mat or woven fabric or roving is positioned manually in the open mold, and resin is poured, brushed, or sprayed over and into the glass plies. Entrapped air is removed manually with squeegees or rollers to complete the laminates structure. Room temperature curing epoxies and polyester are the most commonly used matrix resins. Curing is initiated by a catalyst in the resin system, which hardens the Fiber reinforced resin composite without external heat. For a high quality part surface, a pigmented gel coat is first applied to the mold surface.

20 composite samples were prepared with the dimension of 120 mm x 30 mm x 3 mm using the molding pattern prepared in mild steel. Wax is applied on all surfaces of the mould, which helps to remove the pattern, and to take out the fabricated composite material easily.

As an initial step, catalyzed resin applied on the inner edges of the molding pattern, this step helps the pattern would be fixed. The measured fiber is spreaded on the moulding box. Then epoxy resin is poured on the fiber and it is dipped within the fiber inside the moulding box. Thus 20 samples are prepared through hand lay-up method, the mixture should be spread over all area of the pattern evenly and before pouring the mixture into the mold pattern, the overhead projector (OHP) sheet and wax is used to prevent the sticking of polymers and to get good surface finish. For this hand lay-up method 5 kN load is applied in compression moulding machine and the whole set up was let it as for 24 hours. The obtained composite plate is shown in Fig.3.



Fig.3. Calotropis gigantea stem fiber reinforced composite plate

A 3 mm thick plate was made from the epoxy and hardener taken in the ratio of 100 and 10 parts by weight respectively. Then the moulding box was loaded with the matrix mixture of calotropis and glass fibre with varying percentage for respective samples. After curing, the plate was removed from the moulding box with simple tapering and it was cut into samples. A Hacksaw blade was used to cut each material into smaller pieces, for various experiments. Composite specimen for tensile test is shown in Fig.4.



Fig.4. Composite specimen for tensile test

III. RESULTS AND DISCUSSION

3.1. Tensile Test

The tensile test was performed on all the samples as per ASTM D3039-76 test standards. The tension test is generally performed on flat specimens. A uni-axial load is applied through the ends. The ASTM standard test recommends that the specimens with fibers parallel to the loading direction should be 11.5 mm wide.

Length of the test section should be 120 mm. The test-piece used is having dimensions according to the standards. Among these composites there is a considerable increase of tensile strength peak load 276.49kg/cm² for the hybrid sample-12 as the percentage of glass fibre increases to 12 gm. The experiment was conducted on both samples of calotropis /glass combinations. Three number of specimens were tested for each combination and the average was considered for analysis. 5 sample test results are given in Table 2.

Table 2: Test results

sample	Tensile strength kg/cm ²	Impact strength Joules	Hardness HV	Density g/cc
4	260.78	3.321	87.2	1.005
12	276.49	6.559	95.5	1.012
6	272.55	4.563	92.3	1.013
11	275	6	94.9	1.00
10	272.12	4.67	93.1	1.01

Tensile tested specimens are given in Fig. 5, 6.



Fig.5. Tensile tested composite sample-12



Fig.6. Tensile tested composite sample - 10

3.2. Impact test

Analog Izod/Charpy impact tester is used for testing the impact properties of calotropis fiber reinforced composite specimen. The equipment with a minimum resolution on each scale of 0.02J, 0.05J, 0.1J and 0.2J respectively. Four scales and corresponding hammers (R1, R2, R3, R4) are provided for all the above working ranges.

The impact energy of 20gm weight percentage of calotropis gigantea stem fiber reinforced composites (Sample 12) is 6.559 J which is greater than other samples due to increase in glass fiber content. Fig. 7 shows the tested impact strength sample-6.



Fig.7. Impact tested composite sample - 6

3.3. Hardness test

Hardness is defined as the ability of a material to resist plastic deformation. The test samples with dimensions of 20mm x 20 mm x 3 mm are used for the hardness test conducted on Vicker's hardness testing machine. The proposed composite provides high hardness as 95.5 HV for sample 12 (increasing the composition of fiber from 20 gm to 30 gm and glass fiber to 12 gm).

3.4. Density test

The density of a substance is the relationship between the mass of the substance and how much space it takes up. The test samples with dimensions of 20 mm x 20 mm x 3 mm were used and the density test was conducted on density tester equipment. Fig. 8 shows the density test samples.



Fig.8. Density tested specimens

CONCLUSIONS

To explore new natural materials with high efficiency results in continuous invention. The increase in fiber content gradually increases tensile strength, impact strength and hardness. The highest value of tensile strength for composites containing 30gm calotropis gigantea stem fiber was obtained with addition of 12 gm glass fiber. The above comparison clearly shows the usage of less than 12 gm glass fiber which in turn increases tensile strength, impact, density and hardness. The Izod impact strength significantly decreased to 3.321 J (sample 4) when the glass fiber content is decreased. The resulting properties reveal that composites with good strength could be successfully developed using calotropis gigantea stem fiber.

It is observed from the figure that the surface looks smooth and lesser void content as shown on the

upper surface of the composite sample. This lesser void is actually caused by an excess of resin squeezed during solidification, which causes shortage of resins between two adjacent fibers. Despite the fact this study produce a new natural fiber into the research but has some limitations, this study considered the weight proportion ratio of fiber to composite by 50% each, hence in future this can be extended with various composition using glass fibers.

REFERENCES

1. L.Y. Mwaikambo, and M.P. Ansell, "Chemical modification of hemp, sisal, jute, and kapok fibers by alkalization", *Journal of Applied Polymer Science*, vol.84, no.12, pp.2222–34, 2002.
2. Sunil V Chavan, G.R. Rajkumar, K.P. Ashik, and M.H. Shivalingappa, "Mechanical Properties of Jute fiber reinforced Polyester based composites under different environmental conditions", *Advances in Polymer Science and Technology: An International Journal*, vol. 6, no.2, pp.34–39, 2016.
3. A.P. Sharma, and B.D. Tripathi, "Assessment of atmospheric PAHs profile through calotropis gigantea R.Br. leaves in the vicinity of an Indian coal-fired power plant", *Environmental monitoring and assessment*, vol. 146, pp. 477–482, 2009.
4. J.S. Gamble, "Flora of the Presidency of Madras", Vol. I, II, III, Botanical survey of India, Calcutta, 1935.
5. P. Oudhia, S.S. Kolhe, and R.S. Tripathi, "Allelopathic effects of white top (*Parthenium hysterophorus* L.) on chickpea", *Legume Research*, vol.20, no.2, pp.133–136, 1997.
6. P.J. Roe, and M.P. Ansell, "Jute reinforced polyester composites", *Journal of Material Science*, vol.20, pp. 4015–4020, 1985.
7. J.A. Khan, M.A. Khan, and M.R. Islam, "A study on mechanical, thermal and environmental degradation characteristics of N, dimethylaniline treated jute fabric-reinforced polypropylene composites", *Fibers and Polymers*, vol.15, no.4, pp. 823–830, 2014.
8. T. Karthik, and R. Murugan, "Milkweed-A Potential Sustainable Natural Fibre Crop", *Environmental Footprints and Eco-design of Products and Processes*, pp.111–146, 2016.
9. Nazilla Tarabi, Hossein Mousazadeh, Ali Jafari, and Jalil Taghizadeh - Tameh, "Design, construction and evaluation of a fiber extracting machine from calotropis (milkweed) stems", *Engineering in Agriculture, Environment and Food*, vol.8, no. 2, pp. 88–94, March 2015.
10. G. Dilli Babu, K. Sivajibabu, and P. Nanda kishore, "Tensile and wear behavior of calotropis gigantea fruit fiber reinforced polyester composites", *Procedia Engineering*, vol. 97, pp. 531–535, 2014.
11. Chama Ajay Srinivas, and G. Dilli Babu, "Mechanical and machining characteristics of calotropis gigantea fruit fiber reinforced plastics", *International Journal of Engineering Research & Technology*, vol. 2, no. 6, June 2013.
12. T. Karthik, and P. Ganesan, "Development of eco-friendly textile composites from calotropis gigantea bast fiber", *International Journal of General Engineering and Technology*, vol.1, no. 1, pp. 26–43, Aug 2012.
13. Alireza Ashori, and Zaker Bahreini, "Evaluation of Calotropis gigantea as a Promising Raw Material for Fiber-reinforced Composite", *Journal of composite materials*, vol. 43, issue 11, pp. 1297–1304, 2009.
14. T.A. Theodore, "Introduction to Engineering Statistics and Six Sigma", Springer-Verlag London Limited, 2006.

★ ★ ★